

Metakaolin

Typische Eigenschaften	Metabrite CM70	Metabrite CMC
ppm > 325 mesh	200	0.05 max.
% > 10 Mikrometer	4	
% < 2 Mikrometer	70	60-70
% > 5 Mikrometer		10
% Feuchte	1.0	0.4
Helligkeit (ISO)	87	88±1
Dichte	2.64	2.64
pH	5.0	5.0-6.0
Spezifische Oberfläche (m ² /g)	14	10
% SiO ₂	60	49.7
% Al ₂ O ₃	35	44.4
% Fe ₂ O ₃	0.6	0.3
% TiO ₂	0.9	1.0
% Alkalis		0.1
Quarz		< 0.1%
		Rest: Amorph